## ANDEROL PRODUCT DATA SHEET

## ANDEROL® 1613

Synthetic Gas Engine Lubricant, SAE 40

## GENERAL INFORMATION

ANDEROL 1613 lubricant is ash and anti-wear containing and is designed for use in four-cycle gas engines. This heavy-duty gas engine is formulated with synthetic base stocks combined with a dispersant having excellent high-temperature stability and anti-friction additives that will contribute to improved fuel economy and greater engine life.

Note: ANDEROL 1613 is currently produced on an "on-demand" basis. Please consult us for minimum batch sizes, packages and availability information.

## **TYPICAL PROPERTIES:**

PROPERTY	TEST METHOD	RESULT
SAE Grade	SAE J-300	40
Viscosity, 100°F, SUS	ASTM D-445	865.1
Viscosity, 210°F, SUS	ű	76.3
Viscosity, 40°C, cSt	ű	162.3
Viscosity, 100°C, cSt	ű	14.16
Viscosity Index	ASTM D-2270	82
Flash Point, °C (°F)	ASTM D-92	248 (480)
Fire Point, °C (°F)	ű	285 (545)
Autoignition Temperature °C (°F)	ASTM E-659	427 (800)
Four Ball Wear, 1200 rpm, 75°C, 40 kg, 1 hr, mm	ASTM D-2266	0.40
Copper Corrosion, 24 hrs, 99°C	ASTM D-130	1b
Foaming – Sequence I, II, and III	ASTM D-892	nil
Evaporation, 22 hrs, 99°C	ASTM D-972	0.5
Conradson Carbon Residue, %	ASTM D-189	0.2
Total Acid Number	ASTM D-974	1.0
Total Base Number	ű	6.0
Sulfated Ash, %	ASTM D-8874	0.90
Specific Gravity, 25°C	ASTM D-1298	0.98

This information is furnished without warranty, representation, inducement, or license of any kind, except that it is accurate to the best of OUR knowledge or obtained from sources believed by ANDEROL to be accurate. ANDEROL does not assume any legal responsibility for use of reliance upon it. Only chemists or chemically qualified lab technicians should carry out tests. Before using any chemical, read its label and Material Safety Data Sheet.

<sup>&</sup>lt;sup>®</sup>ANDEROL is a reg. trademark of ANDEROL COMPANY.

A1613: 4/19/02



ANDEROL COMPANY PO Box 518, 215 Merry Lane East Hanover, New Jersey USA

Tel: 888-ANDEROL Or Tel: (973) 887-7410 Fax: (973) 884-3825 E-mail: info2@anderol.com