

## RENEW™ WIRE ROPE OIL

Each time a wire rope bends or flexes, the strands rub together. In addition, the outer strands rub against the sheaves. Renew™ Wire Rope Oil protects the strands and sheaves from friction and wear. This increases wire rope life while decreasing downtime for changeouts. The final result is more production and less cost.

Renew™ Wire Rope Oil is specially formulated to penetrate to the core of the rope. Thus, it lubricates inner rope strands, leaving a nondrying, nontacky film on the rope exterior.

Renew™ Wire Rope Oil contains highly efficient extreme pressure additives to provide maximum load carrying ability. It also provides excellent corrosion protection.

### BENEFITS:

- PROLONGS WIRE ROPE LIFE - readily penetrates to the core and lubricates internal strands.
- NONTACKY - eliminates dirt pick up and lubricant sling off.
- EXTREME LOAD-CARRYING ABILITY - extends wire rope life and minimizes downtime.

### APPLICATIONS:

Whitmore's Renew™ can be used to lubricate all sizes of wire rope as well as chains, leaf springs and other applications where a penetrating oil is needed.

Renew™ can be applied automatically or manually as required. Best results will be obtained if it is applied while the rope passes over a sheave.

ASTM #		TYPICAL CHARACTERISTICS	
		20	30
D-445	<b>Kinematic Viscosity</b> cSt @ 40°C cSt @ 100°C	42.7	60.8
		6.7	9.2
D-2161	<b>Saybolt Viscosity</b> SUS @ 100°F SUS @ 210°F	218	303
		49	57
D-2270	<b>Viscosity Index</b>	111	132
D-97	<b>Pour Point, °F (°C)</b>	-25 (-32)	-15 (-26)
Gardner Method	<b>Density, lb/gal @ 60°F (15.5°C)</b> <b>Specific Gravity, g/cc @ 60°F (15.5°C)</b>	7.54	7.52
		0.905	0.903
D-92	<b>Flash Point, °F (°C)</b> Cleveland Open Cup	335 (168)	335 (168)
D-92	<b>Fire Point, °f (°C)</b> Cleveland Open Cup	350 (177)	350 (177)
D-2782	<b>Timken OK Load, lb</b>	40	40
D-2783	<b>Four Ball EP</b> Weld Point, kg	250	250
D-4172	<b>Four Ball Wear</b> Scar Wear, mm @ 40 kgf	0.53	0.58
D-665	<b>Rust Test</b> Distilled Water Synthetic Sea Water	Pass	Pass
		Pass	Pass
D-130	<b>Copper Strip Corrosion</b> 212°F (100°C) @ 3 hr	1B	1B

*The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.*

### PACKAGING

Shuttle Tanks	Drums	Pails
---------------	-------	-------

For warranty information, scan the QR code.  
You can also email us at [sales@whitmores.com](mailto:sales@whitmores.com)  
Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318  
An ISO 9001 and ISO 14001 registered company • [www.whitmores.com](http://www.whitmores.com)

